

## Lithium-ion Rechargeable Specification

Product name: LiFePO4 battery

Product model: 128-3BP

Specification Approved	PREPARED	
	CHECKED	
	APPROVED	

### Revised List

Version No	Description of Revise	Date	Prepared
A0	New Publish	2024-01-18	

**SHENZHEN HIMAX ELECTRONICS CO.,LTD.**

Add: Building B, Nantong Avenue NO.5, Tongle Community, Baolong Street,  
Longgang Shenzhen China

Tel: 86 (0) 755-25629920 Fax: 86 (0) 755-25629925

[www.himaxelectronics.com](http://www.himaxelectronics.com)

## Content

1. Scope.....	P.3
2. Model.....	P.3
3. Reference standard.....	P.3
4. Specification.....	P.3~4
5. PCM Parameter.....	P.4~5
6. Product Circuit diagram .....	P.5
7. Electrical Performance & test condition .....	P.6
8. Mechanical Performance .....	P.7
9. Cell Safety Performance .....	P.7
10. Delivery/Packing/Storage and Shipment .....	P.8
11. Battery Pack Feature .....	P.8
12. Period of Warranty .....	P.9
13. Warnings .....	P.9
14. Battery operation instruction .....	P.9~10
15. Others .....	P.10

## 1. Scope

This product specification describes HIMAX's LiFePO<sub>4</sub> battery. Please using the test methods that recommend in this specification. If you have any opinions or advice about the test items and methods, please contact us.

## 2. Model

Model: 128-3BP

## 3. Reference standard

The standard reference GB/T18287-2013, UL1642 and CE61960 technology standards compiled.

## 4. Specification

Item		Rating	Note
Cell	Type	LiFePO <sub>4</sub> Battery	
	Cell Model	18650-1500mAh	
	Nominal Capacity	1500mAh	Discharge: 0.2C Cut-off Voltage:2.5V
	Minimum Capacity	1450mAh	Discharge: 0.2C Cut-off Voltage: 2.5V
	Nominal voltage	3.2V	
	Internal Impedance	≤30m Ω	
	Dimension	Max 18.5x65.7mm	
	Weight	Approx 40.7g	
Battery pack	Pack Method	4S2P	
	Nominal Capacity	3000mAh	Discharge: 0.2C Cut-off Voltage:10V
	Minimum Capacity	2900mAh	Discharge: 0.2C Cut-off Voltage: 10V
	Nominal Voltage	12.8V	
	Energy	38.4Wh	
	Charge Voltage	14.4V	
	Discharge cut-off voltage	10V	
	Charge Method	CC/CV	
	Standard Charge Current	0.6A	
	Max. Charge Current	1.5A	
	Standard Discharge Current	0.6A	
	Max. Continues Discharge current	3A	


	Cycle Life	2000 times (次)	80% SOH
	Internal Impedance	≤200mΩ	
	Dimension	Max 537*25*19.1mm	
	Output Wire	UL1015 20AWG	75±5mm
	Connector	Molex 39-01-3023	
	Weight	Approx 355g	
	Working Temperature Range	Charge: 0°C~45°C Discharge: -20°C~60°C	
	Storage Temperature	-10°C~45°C	

## 5. PCM Parameter

No.	Item	Condition	Specification
1	Voltage	Battery charging voltage	14.4V 3.6V*4
2	Balanced	Voltage	3.525±0.035V
		Current	36±10mA
3	Over-charge	Over-Charge Detect Voltage	3.65±0.035V
		Over-Charge Reset Voltage	3.55±0.05V
		Over-Charge Delay Time	0.5-1.5S
4	Over-discharge	Over-Discharge Detect Voltage	2.3V±0.08V
		Over-Discharge Reset Voltage	2.7V±0.1V
		Over-Discharge Delay Time	0.5-1.5S
5	Over-charge-current	Over-Current Detect Current	7±1.5A
		Delay time	300-700ms
6	Over discharge current	Over-Current Detect Current	17±3.5A
		Delay time	0.5-1.5S
7	Short-circuit protection	Short-circuit current	68±14A
		Short detection delay time	100-600uS
		Release Conditions	Cut off load

8	Normal current consumption	Normal current consumption of PCM	$\leq 50\mu\text{A}$
9	Temperature protection	Charging temperature protection	$65 \pm 5^\circ\text{C}$
		Discharge temperature protection	$65 \pm 5^\circ\text{C}$
10	Suggest working conditions	Max.continuous charge current	5A
		Max.continuous discharge current	5A
		Suggest working temperature	$-20-60^\circ\text{C}$
11	IR resistance	IR of PCM	$\leq 100\text{m}\Omega$
12	Dimension	Length	$521 \pm 0.5\text{mm}$
		Width	$14 \pm 0.5\text{mm}$
		Thickness	$2.8 \pm 0.5\text{mm}$

### 6. Product Circuit diagram



## 7. Electrical Performance & test condition

### 7.1 Standard Test Condition

The battery shall be evaluated within 1 month from the arrival date.

Unless otherwise stated in these specifications, the following test shall be carried out in an ambient temperature of  $20\pm 5^{\circ}\text{C}$ , relative humidity of  $65\pm 20\%$ ,

Discharge capacity when the battery is discharged at 0.6A to 10V after being standard charged. Five cycles are permitted for this test. The test shall be terminated at the end of the first cycle which meets the requirement.

### 7.2 Testing Instrument or Apparatus

#### 7.2.1 Dimension Measuring Instrument

The dimension measurement shall be implemented by instruments with equal or more precision scale of 0.01mm specified.

#### 7.2.2 Voltmeter and Ammeter

Voltmeters and ammeters shall be equal or more precision instruments of  $10\text{K}\Omega/\text{V}$  and  $0.01\Omega$ .

#### 7.2.3 Impedance Meter

Impedance shall be measured by a sinusoidal alternating current method (1kHz LCR meter).

### 7.3 Standard Charge

Standard charge means charging for 6hours using 14.4V/0.6A charger.

### 7.4 Standard Discharge

Standard discharge means discharging at 0.6A down to 10V.

### 7.5 Electrical Performance

Item	Condition	Specification
Open-Circuit Voltage	The open-circuit voltage shall be measured within 24hours after standard charge.	$\geq 13.2\text{V}$
Battery Capacity	The discharge time at 0.6A shall be measured after standard charge at $20\pm 5^{\circ}\text{C}$ and rest 30mins.	$\geq 95\%$
Cycle Life	The discharge time on standard discharge shall be measured after 2000 cycles of standard charge and discharge at $20\pm 5^{\circ}\text{C}$ .	$\geq 80\%$
Charge(capacity) retention	The discharge time at 0.6A shall be measured after standard charge and then storage at $20\pm 5^{\circ}\text{C}$ for 28days.	$\geq 95\%$
Temperature Characteristic1	After standard charging at $20\pm 5^{\circ}\text{C}$ , laying the battery at $55^{\circ}\text{C}$ for 2hours, then discharge at 0.6A to 10V, record the discharge time.	$\geq 90\%$
Temperature Characteristic2	After standard charging at $20\pm 5^{\circ}\text{C}$ , laying the battery at $-10^{\circ}\text{C}$ for 4hours, then discharge at 0.6A to 10V, record the discharge time .	$\geq 60\%$

## 8. Mechanical Performance

Item	Condition	Specification
Crush Test	A battery is to be crushed between two flat surfaces. The force for the crushing is to be applied by a hydraulic ram with a 32mm diameter piston. The crushing is to be continued until a pressure reading of 17.2mmPa is reached on the hydraulic ram, applied force of 13kN. Once the maximum pressure has been obtained it is to be released.	No fire, No explosion
Drop Test	The battery has only two axes of symmetry in which case only two directions shall be tested. The battery is to be dropped from a height of 1 meter twice onto concrete ground.	No explosion, No fire, No smoke
Vibration	A full-charged battery is to be subjected to simple harmonic motion with an amplitude of 1.6mm total maximum excursion. The frequency is to be varied at the rate of 1 hertz per minute between 10 and 55 hertz. The cell shall be vibrated for 30 minutes per axis o XYZ axes.	No leakage No Fire No explosion

## 9. Cell Safety Performance

Item	Condition	Specification
Over charge	At 20±5°C, charging battery with constant current 1C to voltage 4V, then with constant voltage 4V till current decline to 0.	No explosion No fire
Over discharge	At 20±5°C, the cell are fully charged with standard charging method and standby at least 1 hour. The cell should be discharged at a current of 1C for 2.5h.	No explosion No fire No leakage
Short-circuit	At 20±5°C, The cells are fully charged with standard charging method and standby at least 1hour. Positive and negative terminal connect with wire (maximum load of 50mΩ) to cause short circuit until its voltage is lower than 0.1V or cell temperature on the surface is back to room temperature ±10°C.	No explosion, No fire The temperature of the surface of the cell are lower than 150°C
Heating	Battery is heated in a circulating air oven at a rate of 5±2°C per min to 130°C, an then placed 30 mins under 130°C.	No explosion, No fire

## 10. Delivery/Packing/Storage and Shipment

10.1 Approx. 30-70% charged before delivery, Shipment voltage: 12.8-13.4V.

10.2 The battery should be checked the voltage, resistance and the function of protective circuit before shipment.

### 10.3 Packing and Shipping


10.3.1 The battery should be transported to the factory assembly, to pay special attention to the packing, in order to avoid transport stress.

10.3.2 The battery should be in a half state of charge packaging boxes for transport, in the transport process, prevent severe vibration, shock, extrusion, prevent the sun and rain, should be in automobile, train, ship, airplane and other forms.

### 10.4 Abnormal Condition

Do not use the battery when it's smell like abnormal cell electrolyte because of transport stress, sag, short circuit or any other.

## 11. Battery Pack Feature



<b>HMS Model</b>	128-3BP			
<b>File No.</b>	HLFGB04 3A00-1485		<b>Signature</b>	<b>Date</b>
<b>Revision</b>	A0	<b>Drawn by</b>	Joan Li	2024-01-18



## 12. Period of Warranty

The period of warranty is one year from the date of shipment. HIMAX guarantees to give a replacement in case of battery with defects proven due to manufacturing process instead of the customer abuse and misuse.

## 13. Warnings

To prevent the possibility of the battery from leaking, heating, fire, Please READ this specification carefully before usage and observe the following precautions:

- Ⓢ When recharging, use the LiFePO4 battery charger specifically for that purpose.
- Ⓢ Do not strike battery with any sharp edge parts, such as Ni-tabs, pins and needles.
- Ⓢ Do not immerse the battery in water and seawater.
- Ⓢ Do not use and leave the battery near a heat source as fire or heater.
- Ⓢ Do not reverse the positive and negative terminals.
- Ⓢ Do not connect the battery to an electrical outlet.
- Ⓢ Do not discard the battery in fire or heat it.
- Ⓢ The battery tabs are not so stubborn especially for aluminum tab. Do not bend tab.
- Ⓢ Do not short-circuit the battery by directly connecting the positive and negative terminal with metal object.
- Ⓢ Do not transport and store the battery together with metal objects such as necklaces, hairpins etc.
- Ⓢ Do not knock or throw, trampling battery etc.
- Ⓢ Do not directly solder the battery and pierce the battery with a nail or other sharp object.
- Ⓢ Do not split the battery without permission.

## 14. Battery operation instruction

### 14.1 Charging

Charging current: Do not surpass the biggest charging current which in this specification.

Charging voltage: Do not surpass the highest voltage which in this specification.

Charge temperature: The charge temperature is in according to this specification.

### 14.2 Discharging

Discharge current: Do not surpass the biggest discharge current which in this specification.

Discharging with a higher current may result in the capacity fade and over-heat.

Discharge temperature: The discharge temperature is in according to this specification.

### 14.3 Over-discharges

After the short time excessively discharges charges immediately cannot affect the use, but the long

time excessively discharges can cause the battery the performance, battery function losing. The battery long-term has not used, has the possibility to be able to be at because of its automatic flashover characteristic certain excessively discharges the condition, for prevented excessively discharges the occurrence, the battery should maintain the certain electric quantity.

#### **14.4 Storing the Batteries**

*The battery should store in the product specification book stipulation temperature range. If has surpasses above for 3 months the long time storage, suggested you should carry on additional charge to the battery.*

14.5 Please do not continuously charge the battery over 8hours.

#### **15.Others**

◎The customer is requested to contact HIMAX in advance, if and when the customer needs other applications or operating conditions than those described in this document. Additional experimentation may be required to verify performance and safety under such conditions.

◎HIMAX will take no responsibility for any accident when the battery is used under other conditions than those described in this Document.

◎HIMAX will inform, in a written form, the customer of improvement(s) regarding proper use and handing of the battery, if it is deemed necessary.